

KÖSTER KSK Primer SP

Technical guideline / Article number **7.30**
Issued: February 14, 2013

Solvent containing synthetic resin primer for the substrate preparation for KÖSTER KSK membranes

Features

KÖSTER KSK Primer SP is a solvent containing synthetic resin primer. It can be applied at temperatures down to $-10\text{ }^{\circ}\text{C}$.

Technical data

Active ingredients	20 %
Minimum application temperature	$-10\text{ }^{\circ}\text{C}$
Density	0.90 g / cm^3
Curing time (at $-5\text{ }^{\circ}\text{C}$)	45 min

Field of application

KÖSTER KSK Primer SP can be used to prepare substrates for the application of KÖSTER KSK membranes, in particular at low temperatures (down to $-10\text{ }^{\circ}\text{C}$).

Substrate preparation

The substrate has to be free of loose particles, dust, oil, and grease.

Application

KÖSTER KSK Primer SP is applied by roll or brush in one layer to the whole surface. It is absolutely necessary to check if the primer has fully cured before applying KÖSTER KSK membranes.

Consumption

Approx. 100 ml / m^2 (in case of strongly absorbent substrates, two coats are necessary – total consumption approx. 200 ml / m^2)

Cleaning of tools

Clean tools immediately after use with KÖSTER Universal Cleaner.

Packaging

5 l canister

Storage

In originally sealed packages the material can be stored for approx. 12 months. Observe the regulations for the storage of flammable liquids.

Safety precautions

Wear solvent resistant protective gloves and goggles when working with the material. Work only in properly ventilated areas.

Technical guidelines cited

KÖSTER Universal Cleaner

Art. Nr. 9.01

KÖSTER KSK membranes

Product group. 10.

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.